

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 771 629 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
07.05.1997 Bulletin 1997/19

(21) Application number: 96307932.2

(22) Date of filing: 31.10.1996

(51) Int Cl.⁶: **B29B 7/00**, B29B 7/46,
B29B 7/48, B01F 3/08,
C08J 3/03, C08L 83/04,
A61K 7/48

(84) Designated Contracting States:
DE FR GB

(30) Priority: 01.11.1995 JP 284909/95

(71) Applicant: **Dow Corning Toray Silicone Company Ltd.**
Ichihara-shi, Chiba Prefecture (JP)

(72) Inventors:
• **Hosokawa, Hidehiko,**
Dow Corn. Toray Silic. Co, Ltd
Chiba Prefecture (JP)

• **Maeshima, Junichi,**
Dow Corn. Toray Silic. Co, Ltd
Chiba Prefecture (JP)
• **Suto, Fumitaka, Dow Corn. Toray Silic. Co, Ltd**
Chiba Prefecture (JP)

(74) Representative: **Lewin, John Harvey et al**
Elkington and Fife,
Prospect House,
8 Pembroke Road
Sevenoaks, Kent TN13 1XR (GB)

(54) Method for continuously emulsifying organopolysiloxane gums

(57) A method of continuous emulsification that can emulsify high-viscosity organopolysiloxane gums and is capable of continuous mass production. A compounding extruder is used whose barrel 1 contains at least 2 mixing element-equipped shafts 3 installed in parallel. On each shaft elevations and depressions are formed along the axial direction and the elevations and depressions on respective shafts intermesh. Organopolysi-

loxane gum, emulsifying agent, and water are continuously supplied as starting materials to this compounding extruder, and an organopolysiloxane-in-water emulsion is produced by mixing and homogenizing the starting materials by subjecting them through rotation of the mixing element-equipped shafts to a shearing action at a shear rate of at least 10/second (i.e. 10 reciprocal seconds).

EP 0 771 629 A1

Description

This invention relates to a method for continuously emulsifying organopolysiloxane gums. More particularly, this invention relates to a method that is capable of the continuous emulsification of organopolysiloxane gums that have been difficult to emulsify due to their very high degrees of polymerization.

Emulsions of organopolysiloxanes are widely used in industry as lubricants, release agents including mold-release agents, fiber-treatment agents, glass fiber-treatment agents, cosmetic bases, lustrants, and paint additives. These organopolysiloxane emulsions are prepared by mixing an emulsifying agent and water into a starting fluid organopolysiloxane gum. However, conversion into an emulsion can be a problem as the viscosity of the organopolysiloxane rises, resulting in a corresponding increasing difficulty of emulsification.

Japanese Patent Publication Number Sho 59-51565 [51,565/1984] proposes a method for emulsification of such high-viscosity organopolysiloxanes. This method uses a cylindrical container, and installed therein, a mixing element comprising at least 3 disks placed at fixed intervals on a rotating shaft. Shearing and stirring are conducted by rotation of the mixing element. However, the use of at least 3 disks in this method installed on the rotating shaft coaxially and with a narrow interposed gap, limits the viscosity of organopolysiloxanes that can be mixed across these closely spaced disks, to at most about 70,000 centistokes. It is not practical to emulsify organopolysiloxanes with higher viscosities using this method.

The object of our invention in contrast is to provide a highly productive method for continuous emulsification of organopolysiloxane gums that is capable of continuous mass production, and that can emulsify even high-viscosity organopolysiloxane gums heretofore difficult to emulsify.

These and other objects will become apparent from a consideration of the detailed description.

Figure 1 is a schematic longitudinal cross-sectional view of a compounding extruder used to carry out the method of our invention for continuous emulsification of organopolysiloxane gums.

Figure 2 is a cross-sectional side view taken along section line 2-2 in Figure 1.

Figures 3A, 3B, and 3C are views showing the changes in position of the mixing element-equipped shafts during operation of the compounding extruder of Figure 1.

The reference numbers used in these figures correspond to the various elements as follows: 1 is the barrel, 2 is the rotating shaft, 3 is the mixing element-equipped shaft, 3a is the paddle, 3s is the screw, 4 is the supply port, and 5 is the discharge port.

Our invention is characterized by continuously feeding an organopolysiloxane gum, an emulsifying agent, and water, as starting materials into the supply

port of a compounding extruder whose barrel contains at least 2 mixing element-equipped shafts installed in parallel. On each shaft, elevations and depressions are formed along the axial direction in alternating sequence, and the elevations and depressions on one shaft intermesh with the elevations and depressions on the second shaft. An organopolysiloxane-in-water emulsion is produced by mixing and homogenizing the starting materials by subjecting them through rotation of the mixing element-equipped shafts to a shearing action at a shear rate of at least 10/second; and discharging the emulsion from the discharge port of the compounding extruder.

Mixed and homogenized emulsions of high-viscosity organopolysiloxane gums can be easily prepared due to application to the starting materials of a shearing action at a shear rate of at least 10/second, and due to the above-described arrangement in which at least 2 mixing element-equipped shafts having elevations and depressions along the axial direction, are installed in parallel within the barrel, and the elevations and depressions on one shaft intermesh with the corresponding elevations and depressions on the second shaft.

The "shear rate" according to our invention is defined by the formula:

$$\text{shear rate } V_s \text{ (1/sec.)} = V/t$$

wherein V is the peripheral velocity at the outer surface of the mixing element-equipped shaft in cm/sec., and t is the minimum clearance in cm between the outer surface of the mixing element-equipped shaft and the interior wall of the barrel.

Our method can be explained more fully by reference to the compounding extruder as depicted in the drawings. Thus, Figures 1 and 2 depict a compounding extruder for carrying out the method of our invention for continuously emulsifying organopolysiloxane gums. In Figures 1 and 2, 1 is a barrel whose axis is fixed on the horizontal, and whose interior space has an 8-shaped transverse cross-section (i.e., transverse cross-section normal to the axial direction). A starting material supply port 4 is fixed to the top of one end of the barrel 1, and a discharge port 5 is fixed at the bottom of the other end of the barrel 1, for discharge of the emulsion made by the mixing operation.

Two mixing element-equipped shafts 3 are inserted in parallel, on the left and right respectively, in the interior space of the barrel 1 with 8-shaped transverse cross-section. These shafts are set up to be driven in the same direction as indicated by the arrows with motors not shown in the drawings.

In the arrangement of these mixing element-equipped shafts 3 moving from upstream at the supply port 4 to downstream at the discharge port 5, a plural number of lens-shaped paddles 3a are first stacked on the rotating shaft 2 moving along the axial direction followed by installation of a screw 3s. The plural number

of paddles 3a makes up the major portion of the mixing mechanism. Both ends of the lens-shape lie in close proximity to the interior surface of the barrel 1 and are separated therefrom by a small clearance t. A small clearance t similarly exists for the periphery of the screw 3s.

The paddles 3a are attached on the rotating shaft 2 as groups, consisting in each case of 2-4 paddles with the same angle, and the attachment angle can be changed in 45° increments between the groups. The axial and alternating sequence of elevations and depressions on the mixing element-equipped shaft 3 is formed by changing the phase between the attachment angles of the multi-element groups. In addition, the elevations and depressions formed along the axial direction in alternating sequence on a mixing element-equipped shaft 3, intermesh with the elevations and depressions on a neighboring parallel mixing element-equipped shaft 3.

At least 2 mixing element-equipped shafts 3 must be present, and the elevations and depressions on neighboring shafts must intermesh. Three or more mixing element-equipped shafts may be installed, but the intermeshing relationship must be preserved. The attachment angles of the multi-paddle 3a groups are not necessarily staggered in 45° increments on the rotating shaft 2, and other increments can be used such as 15° or 30°.

In addition to the organopolysiloxane gum, water and the emulsifying agent are also mixed as starting materials in the continuous emulsification of the organopolysiloxane gum using the compounding extruder described above. These three starting materials may be introduced separately into the supply port 4, or they may be preliminarily mixed, and the resulting mixture may be introduced into the supply port 4.

Due to the different attachment angles for the multi-paddle 3a groups on the 2 mixing element-equipped shafts 3, and the elevation/depression intermeshing of reciprocal paddles 3a between the two shafts, the starting materials are subjected to a mixing action and a shearing action within the compounding extruder as the intermesh configuration of the paddles 3a changes as shown in Figures 3A-3C. In addition, because both tips of the lens-shaped paddles 3a generate a shearing action by virtue of the small clearance t with the inner wall of the barrel 1, the three starting materials are subjected to additional strong mixing and homogenizing activities that serve to generate a microparticulate emulsion. The mixture thereby emulsified by the paddles 3a is finally discharged through the discharge port 5 while being subjected to additional mixing by the downstream screw 3s.

In applying the mixing action described above, the shear rate in the shearing action (i.e., between paddles and between the paddle tips and barrel interior wall) must be at least 10/sec., and is preferably at least 100/sec. Ahomogeneous microparticulate emulsion cannot be obtained when the shear rate applied to the


mixture is less than 10/sec.

In addition, the compounding extruder is preferably arranged in such a manner that the ratio L/D is at least 5, and more preferably at least 10, wherein L is the axial length of the mixing element-equipped shaft within the barrel 1, and D is the diameter of rotation of the peripheral surface of the paddles 3a. The clearance t between the paddles 3a or screw 3s and the interior wall of the barrel 1 preferably is no greater than 5 mm.

High-viscosity organopolysiloxane gums with viscosities at 25°C in excess of 500,000 centipoise can be used as the starting organopolysiloxane gum (i.e., Component A) for emulsification in our continuous emulsification method. Even when the viscosity of the organopolysiloxane is higher, it can still be easily emulsified by dissolving it in a solvent.

Any organopolysiloxane which is a gum at ambient temperature can be used. The plasticity of the organopolysiloxane gum is measured at 25°C by the method described in Japanese Industrial Standard JIS C2123, and is at least 0.75 mm, preferably 1.0-2.5 mm.

Organopolysiloxane gums suitable for our invention can be illustrated by the formula:



wherein R is a substituted or unsubstituted monovalent hydrocarbon group. R can be an alkyl group such as methyl, ethyl, and propyl; an aryl group such as phenyl and tolyl; and such groups in which all or part of the hydrogen has been replaced by halogen, such as chloromethyl and 3,3,3-trifluoropropyl. a has a value from 1.9-2.1.

Such organopolysiloxane gums are exemplified by trimethylsiloxy-endblocked dimethylpolysiloxane gums, silanol-endblocked dimethylpolysiloxane gums, trimethylsiloxy-endblocked dimethylsiloxane-phenylmethylsiloxane copolymer gums, silanol-endblocked dimethylsiloxane-phenylmethylsiloxane copolymer gums, trimethylsiloxy-endblocked dimethylsiloxane-diphenylsiloxane copolymer gums, silanol-endblocked dimethylsiloxane-diphenylsiloxane copolymer gums, trimethylsiloxy-endblocked dimethylsiloxane-methyl (3,3,3-trifluoropropyl) siloxane copolymer gums, and silanol-endblocked dimethylsiloxane-methyl (3,3,3-trifluoropropyl)siloxane copolymer gums.

The molecular structure of the organopolysiloxane gum can be linear, partially branched and linear, or a network. A linear organopolysiloxane gum is preferred. Additives such as silica micropowder can be present in the organopolysiloxane gum so long as the object of the invention is not compromised.

Water (Component B) can be tap water or ion-exchanged water.

Component B is admixed at the rate of 1-400 weight parts per 100 weight parts of organopolysiloxane gum Component A.

Emulsifying agent (Component C) can be a nonionic, anionic, or cationic surfactant. Nonionic surfactants are exemplified by polyoxyalkylene alkyl ethers, polyoxyalkylene alkylphenol ethers, polyoxyalkylene alkyl esters, polyoxyalkylene sorbitan alkyl esters, polypropylene glycol, and diethylene glycol. Anionic surfactants are exemplified by fatty acid salts such as sodium laurate, sodium stearate, sodium oleate, and sodium linolenate; alkylbenzenesulfonic acids such as hexylbenzenesulfonic acid, octylbenzenesulfonic acid, and dodecylbenzenesulfonic acid; salts of the preceding; alkylsulfonates; and sodium polyoxyethylene alkylphenyl ether sulfate. Cationic surfactants are exemplified by octyltrimethylammonium hydroxide, dodecyltrimethylammonium hydroxide, alkyltrimethylammonium chlorides, and benzylammonium salts. Two or more of these surfactants may be used in combination.

Component C is added in sufficient quantity to thoroughly emulsify organopolysiloxane gum Component A in the water Component B. In specific terms, Component C is preferably blended at from 0.1-100 weight parts per 100 weight parts of organopolysiloxane gum Component A.

Organopolysiloxane gum emulsions prepared by our continuous emulsification method are generally obtained in the form of emulsions in which the organopolysiloxane gum is emulsified and dispersed in water. These emulsions generally have an average particle size in the range from 0.1-50 micrometers.

An organopolysiloxane gum emulsion adapted to a particular application or end use can be obtained either by the direct use of the organopolysiloxane gum emulsion as prepared, or by diluting the product with water. These emulsions can be used as fiber-treatment agents, lubricants, release agents including mold-release agents, glass fiber-treatment agents, cosmetic oil bases, lustrants, defoamers, and paint additives.

Example

The following ingredients were continuously supplied to the compounding extruder depicted in Figures 1 and 2: 100 weight parts of a trimethylsiloxy-end-blocked dimethylpolysiloxane gum with a viscosity at 25°C of 10 million centipoise; 10.0 weight parts polyoxyethylene lauryl ether (i.e., a 6 mol ethylene oxide adduct); and 5.0 weight parts ion-exchanged water. These ingredients were sheared and mixed in the compounding extruder, and yielded an emulsion of the dimethylpolysiloxane gum.

The L/D ratio for the compounding extruder employed was 10 wherein L was the length L of the barrel interior (i.e., the mixing element-equipped shaft) and D was the diameter of rotation of the paddles. The minimum clearance for this compounding extruder was 0.1 cm. The mixing element-equipped shaft was rotated at 340 rpm, which provided a shear rate of 890/sec.

The dimethylpolysiloxane emulsion was a translu-

cent paste-like emulsion in which the dimethylpolysiloxane gum was uniformly dispersed and emulsified in water. The emulsion contained an average particle size of 9.9 micrometers of dimethylpolysiloxane gum as measured after dilution with water using a laser light scattering instrument for measuring particle size distribution.

As can be seen from the above description, our continuous emulsification method can emulsify high-viscosity organopolysiloxane gums previously difficult to emulsify, and it can accomplish this continuously and efficiently at high levels of production.

Other variations may be made in compounds, compositions, apparatus, and methods described without departing from the essential features of the invention. The forms of invention are exemplary and not limitations on its scope as defined in the claims.

Claims

1. A method for continuously emulsifying organopolysiloxane gums comprising continuously feeding an organopolysiloxane gum, an emulsifying agent, and water, as starting materials into a compounding extruder having a supply port and a discharge port, the compounding extruder having a barrel which contains at least two mixing element-equipped shafts arranged in parallel, each shaft having elevations and depressions formed along the axial direction in alternating sequence, the elevations and depressions on one shaft intermeshing with the elevations and depressions on the other shaft; producing an organopolysiloxane-in-water emulsion by mixing and homogenizing the starting materials by subjecting the starting materials, through rotation of the mixing element-equipped shafts, to a shearing action at a shear rate of at least 10/second; and discharging the emulsion from the discharge port of the compounding extruder.
2. A method according to Claim 1 wherein the barrel of the compounding extruder has an eight-shaped transverse cross-section when viewed perpendicular to the axial direction of the shafts.
3. A method according to Claim 2 wherein the elevations and depressions along the axial direction of the mixing element-equipped shafts are formed by a plurality of lens-shaped paddles on the shafts.
4. A method according to Claim 3 wherein the downstream side of the mixing element-equipped shafts includes a screw.
5. A method according to Claim 4 wherein the L/D ratio of the mixing element-equipped shafts is at least five, in which L is the length within the barrel of the

mixing element-equipped shafts and D is the diameter of the shafts.

6. A method according to Claim 5 wherein the organopolysiloxane gum has a plasticity at 25°C of at least 0.75 mm, plasticity being determined according to Japanese Industrial Standard C2123. 5
7. A method according to Claim 5 wherein the organopolysiloxane gum has a viscosity of 500,000-10,000,000 centipoise at 25°C. 10
8. A method according to Claim 1 wherein the starting materials include 0.1-100 weight parts of emulsifying agent, 1-400 weight parts of water, and 100 weight parts of the organopolysiloxane gum. 15
9. Apparatus for continuously emulsifying organopolysiloxane gums comprising a compounding extruder having a supply port for continuously feeding an organopolysiloxane gum, an emulsifying agent, and water as starting materials, and a discharge port for discharging an emulsion, the compounding extruder having a barrel which contains at least two mixing element-equipped shafts arranged in parallel, each shaft having elevations and depressions formed along the axial direction in alternating sequence, the elevations and depressions on one shaft intermeshing with the elevations and depressions on the other shaft; the compounding extruder producing an organopolysiloxane-in-water emulsion by mixing and homogenizing the starting materials by subjecting the starting materials, through rotation of the mixing element-equipped shafts, to a shearing action at a shear rate of at least 10/second. 20 25 30 35
10. Apparatus according to Claim 9 wherein the barrel of the compounding extruder has an eight-shaped transverse cross-section when viewed perpendicular to the axial direction of the shafts. 40
11. Apparatus according to Claim 10 wherein the elevations and depressions along the axial direction of the mixing element-equipped shafts are formed by a plurality of lens-shaped paddles on the shafts. 45
12. Apparatus according to Claim 11 wherein the downstream side of the mixing element-equipped shafts includes a screw. 50
13. Apparatus according to Claim 12 wherein the L/D ratio of the mixing element-equipped shafts is at least five, in which L is the length within the barrel of the mixing element-equipped shafts and D is the diameter of the shafts. 55
14. Apparatus for continuously emulsifying organopol-

ysiloxane gums comprising a compounding extruder having a supply port for continuously feeding an organopolysiloxane gum, an emulsifying agent, and water as starting materials, and a discharge port for discharging an emulsion, the compounding extruder having a barrel with an eight-shaped transverse cross-section, the barrel containing at least two mixing element-equipped shafts arranged in parallel, each shaft having elevations and depressions formed along the axial direction in alternating sequence, the elevations and depressions on one shaft intermeshing with the elevations and depressions on the other shaft; the elevations and depressions being formed by a plurality of lens-shaped paddles on the shafts; the downstream side of the mixing element-equipped shafts including a screw; the compounding extruder producing organopolysiloxane-in-water emulsions by mixing and homogenizing the starting materials by mixing and homogenizing the starting materials and subjecting the starting materials, through rotation of the mixing element-equipped shafts, to a shearing action at a shear rate of at least 10/second.




Fig. 1




Fig. 2

Fig 3A




Fig 3B





Fig 3C





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 30 7932

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	US 5 302 658 A (GEE RONALD P ET AL) 12 April 1994 * column 4, line 54 - column 4, line 66; claim 1 *	1-14	B29B7/00 B29B7/46 B29B7/48 B01F3/08 C08J3/03 C08L83/04 A61K7/48
X	GB 2 079 300 A (GEN ELECTRIC) 20 January 1982 * page 2, line 42 - page 2, line 49 * * page 4, line 40 * * page 4, column 58 *	1-14	
P,X	US 5 466 746 A (GECK MICHAEL ET AL) 14 November 1995 * column 1, line 53 - column 1, line 67 * * column 7, line 30 *	1-14	
Y	DE 41 15 531 A (TOSOH CORP) 21 November 1991 * figures 1,2 *	1-14	
D,Y	PATENT ABSTRACTS OF JAPAN vol. 005, no. 184 (C-080), 21 November 1981 & JP 56 109227 A (SHIN ETSU CHEM CO LTD), 29 August 1981, * abstract *	1-14	TECHNICAL FIELDS SEARCHED (Int.Cl.6) B29B B01F C08J C08L A61K
A	GB 1 174 219 A (WERNER AND PFLEIDERER) 17 December 1969 * claim 1; figures 3-5 *		
A	US 4 814 376 A (TANAKA MASAKI ET AL) 21 March 1989 * claim 1; figures 1-3 *		
A	EP 0 463 431 A (DOW CORNING) 2 January 1992 * page 1, line 1 - page 1, line 50 *		
		-/--	
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 29 January 1997	Examiner Kofoed, J
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>* : member of the same patent family, corresponding document</p>			

EPO FORM 1503 (01.92) (P/01.92)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 30 7932

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	EP 0 579 458 A (DOW CORNING) 19 January 1994 * claim 1; example 1 * ---		
A	EP 0 423 759 A (MITSUBISHI RAYON CO) 24 April 1991 * figures 1-6 * -----		
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 29 January 1997	Examiner Kofoed, J
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPN FORM 150 (12.92) (P&C/D)

THIS PAGE BLANK (USPTO)